

Next Nylon 66 Prime Series PGF25-01ABK

Polyamide 66

Next Polymers Ltd.

Message:

Description

PA66 Glass Fiber Reinforced FR Black Compound

Product Applications

This Red Phosphorous Flame retardant grades provides robust UL-94 V0 and a full UL Yellow card. This grade is suitable for molding insulating parts for electrical devices, and more generally for a thin parts under stress.

Benefits

High Mechanical Properties, Low optical density of smokes & High stiffness.

General Information				
Filler / Reinforcement		Glass fiber reinforced material, 25% filler by weight		
Features		Low Optical Density		
		Rigidity, high		
		Flame retardancy		
Uses		Thin wall parts		
		Electrical components		
		Electronic insulation		
Agency Ratings		EC 1907/2006 (REACH)		
RoHS Compliance		RoHS compliance		
Appearance		Black		
Processing Method		Injection molding		
Physical	Dry	Conditioned	Unit	Test Method
Specific Gravity	1.38	--	g/cm ³	ASTM D792
Molding Shrinkage				ASTM D955
Flow	0.50	--	%	ASTM D955
Transverse flow	0.90	--	%	ASTM D955
Water Absorption				ASTM D570
23°C, 24 hr	0.75	--	%	ASTM D570
Saturation ¹	6.2	--	%	ASTM D570
Hardness	Dry	Conditioned	Unit	Test Method
Rockwell Hardness				ASTM D785
Class m	105	--		ASTM D785
Class r	125	--		ASTM D785
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Strength	140	110	MPa	ASTM D638
Tensile Elongation (Break)	4.0	5.0	%	ASTM D638
Flexural Modulus	7800	6200	MPa	ASTM D790

Flexural Strength	220	160	MPa	ASTM D790
Impact	Dry	Conditioned	Unit	Test Method
Notched Izod Impact (23°C)	88	120	J/m	ASTM D256
Thermal	Dry	Conditioned	Unit	Test Method
Deflection Temperature Under Load				ASTM D648
0.45 MPa, not annealed	260	--	°C	ASTM D648
1.8 MPa, not annealed	250	--	°C	ASTM D648
Melting Temperature	262	--	°C	ASTM D2117
Electrical	Dry	Conditioned	Unit	Test Method
Surface Resistivity	1.0E+13	1.0E+12	ohms	IEC 60093
Volume Resistivity	1.0E+17	1.0E+15	ohms·cm	IEC 60093
Dielectric Strength	26	25	kV/mm	IEC 60243-1
Comparative Tracking Index	600	--	V	IEC 60112
Flammability	Dry	Conditioned	Unit	Test Method
Flame Rating (0.800 mm)	V-0	--		UL 94
Additional Information				
干燥				
This grade is not suitable for food contact, medical devices or toy applicationsPossible Formation of Phosphates in Humid warm environments				
Injection	Dry	Unit		
Drying Temperature - Hot Air Dryer	80.0		°C	
Drying Time	4.0 - 6.0		hr	
Suggested Max Moisture	0.20		%	
Rear Temperature	270 - 275		°C	
Middle Temperature	275 - 280		°C	
Front Temperature	275 - 280		°C	
Mold Temperature	70.0 - 100		°C	
NOTE				
1.	Immersed			

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT