

Badatron® PPS GF30 TF/SIM15

Polyphenylene Sulfide

Bada AG

Message:

30% glasfibres filled tribological injection moulding grade; Low friction and wear at high high service temperature

General Information			
Filler / Reinforcement	Glass fiber reinforced material, 30% filler by weight		
Features	Low friction coefficient		
	Thermal stability, good		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Density (23°C)	1.62	g/cm ³	ISO 1183
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus (23°C)	11500	MPa	ISO 527-2/1
Tensile Stress (Break, 23°C)	160	MPa	ISO 527-2/5
Tensile Strain (Break, 23°C)	1.7	%	ISO 527-2/5
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength ¹ (23°C)	7.0	kJ/m ²	ISO 179/1eA
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature ² (1.8 MPa, Unannealed, 4.00 mm)	270	°C	ISO 75-2/A
Melting Temperature (DSC) ³	295	°C	ISO 3146
Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94
0.8 mm	V-0		UL 94
1.6 mm	V-0		UL 94
Glow Wire Flammability Index			IEC 60695-2-12
0.75 mm	960	°C	IEC 60695-2-12
1.6 mm	960	°C	IEC 60695-2-12
Glow Wire Ignition Temperature			IEC 60695-2-13
0.75 mm	960	°C	IEC 60695-2-13
1.6 mm	960	°C	IEC 60695-2-13
Injection	Nominal Value	Unit	
Drying Temperature	140	°C	
Drying Time	3.0 - 4.0	hr	
Processing (Melt) Temp	300 - 340	°C	
Mold Temperature	140 - 180	°C	
NOTE			

1.	80x10x4 mm
2.	110x10x4 mm
3.	Compound for molding, 10k/min

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

