

# LNP™ LUBRICOMP™ KL002 compound

Acetal (POM) Copolymer

SABIC Innovative Plastics

Message:

LNP LUBRICOMP KL002 is a compound based on Acetal Copolymer resin containing 10% PTFE. Added feature of this material is: Wear Resistant.  
Also known as: LNP\* LUBRICOMP\* Compound KL-4020  
Product reorder name: KL002

General Information			
Additive	PTFE Lubricant (10%)		
Features	Good Wear Resistance		
	Lubricated		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.45	g/cm³	ASTM D792
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus <sup>1</sup>	2550	MPa	ASTM D638
Tensile Strength (Break)	49.0	MPa	ASTM D638
Tensile Elongation (Break)	9.7	%	ASTM D638
Flexural Modulus	2370	MPa	ASTM D790
Flexural Strength	68.9	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	53	J/m	ASTM D256
Unnotched Izod Impact (23°C)	560	J/m	ASTM D4812
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed, 3.20 mm)	92.2	°C	ASTM D648
Injection	Nominal Value	Unit	
Drying Temperature	82.2	°C	
Drying Time	4.0	hr	
Rear Temperature	177 to 188	°C	
Middle Temperature	193 to 204	°C	
Front Temperature	210 to 221	°C	
Processing (Melt) Temp	199 to 216	°C	
Mold Temperature	82.2 to 110	°C	
Back Pressure	0.172 to 0.344	MPa	
Screw Speed	30 to 60	rpm	
NOTE			

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519  
Phone: +86 13424755533  
Email: sales@su-jiao.com  
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

