Keliren® CM352L

Chlorinated Polyethylene

Hangzhou Keli Chemical Co., Ltd.

Message:

Physical

Chlorine Content

Mooney Viscosity (ML 1+4, 121°C)

Keliren® elastomers called rubber grades of CPE products are formulated into quality extruded, molded, and sheet rubber goods that satisfy critical needs for heat, oil and chemical resistance, compression set, toughness and durability, processibility, and value-related economics.

Application: Wire & Cable, Hose, etc

Performance: Low Mooney viscosity, excellent processability

General Information	
Features	Durable
	Flame Retardant
	Good Chemical Resistance
	Good Processability
	Good Toughness
	Good Weather Resistance
	High Heat Resistance
	Low Temperature Resistant
	Low Viscosity
	Oil Resistant
	Ozone Resistant
	Soft
Uses	Appliances
	Automotive Applications
	Cable Jacketing
	Computer Components
	Conveyors
	Hose
	Marine Applications
	Mining Applications
	Sheet
	Wire & Cable Applications
Processing Method	Extrusion
	Injection Molding
	Sheet Extrusion

Nominal Value

50 to 60

34.0 to 36.0

Test Method

ISO 289

ISO 7725

Unit

MU

wt%

Hardness	Nominal Value	Unit	Test Method
Shore Hardness (Shore A)	< 57		ISO 7619
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress (Break)	> 8.00	MPa	ISO 37
Tensile Elongation (Break)	> 700	%	ISO 37

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

