# SILVER® EUL105-K/UL1007

### Polyvinyl Chloride

Guangdong Silver Age Sci & Tech. Co., Ltd

#### Message:

SILVER® PVC for Wire and Cable is produced based on high quality PVC resin by adding modified additives. The modified plastic entirely conforming to RoHS is of excellent mechanical and processing properties. In addition, the custom-made products should be developed by buyers 'requirements in order to meet special usage.

| General Information          |                           |                          |  |
|------------------------------|---------------------------|--------------------------|--|
| Additive                     | Unspecified Additive      |                          |  |
| Uses                         | Wire & Cable Applications |                          |  |
| RoHS Compliance              | RoHS Compliant            |                          |  |
| Physical                     | Nominal Value             | Unit                     |  |
| Specific Gravity             | 1.41 to 1.45              | g/cm³                    |  |
| Hardness                     | Nominal Value             | Unit                     |  |
| Durometer Hardness (Shore A) | 86 to 90                  |                          |  |
| Mechanical                   | Nominal Value             | Unit                     |  |
| Tensile Strength             |                           |                          |  |
| 1                            | > 13.4                    | MPa                      |  |
|                              | > 12.1                    | MPa                      |  |
| Tensile Elongation           |                           |                          |  |
| Break <sup>2</sup>           | > 140                     | %                        |  |
| Break                        | > 180                     | %                        |  |
| Thermal                      | Nominal Value             | Unit                     |  |
| Cold Bend <sup>3</sup>       | -20.0                     | °C                       |  |
| Insulation Resistance        | > 10.0                    | Mohms·km                 |  |
| Burning Behavior             | VW-1                      |                          |  |
| Temperature Resistance       | 105                       | °C                       |  |
| NOTE                         |                           |                          |  |
| 1.                           | after aging (136°C/168h)  | after aging (136°C/168h) |  |
| 2.                           | after aging (136°C/168h)  |                          |  |
| 3.                           | 4H                        |                          |  |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

