

Ultraform® N 2640 Z2

Acetal (POM) Copolymer + PUR
BASF Corporation

Message:

Elastomer-modified injection molding grade with high impact strength for clips, snap and fastening elements, and also for components subject to impact stress.

General Information			
UL YellowCard	E36632-531684	E41871-233597	
Additive	Impact modifier		
Features	Impact modification		
	Impact resistance, high		
Uses	Fasteners		
Agency Ratings	EC 1907/2006 (REACH)		
RoHS Compliance	RoHS compliance		
Forms	Particles		
Processing Method	Injection molding		
Multi-Point Data	Isochronous Stress vs. Strain (ISO 11403-1)		
	Isothermal Stress vs. Strain (ISO 11403-1)		
	Secant Modulus vs. Strain (ISO 11403-1)		
	Shear Modulus vs. Temperature (ISO 11403-1)		
	Specific Heat vs. Temperature (ISO 11403-2)		
	Specific Volume vs Temperature (ISO 11403-2)		
	Viscosity vs. Shear Rate (ISO 11403-2)		
Resin ID (ISO 1043)	POM-HI		
Physical	Nominal Value	Unit	Test Method
Density	1.37	g/cm³	ISO 1183
Melt Volume-Flow Rate (MVR) (190°C/2.16 kg)	7.00	cm³/10min	ISO 1133
Molding Shrinkage			ISO 294-4
Vertical flow direction	1.9	%	ISO 294-4
Flow direction	1.9	%	ISO 294-4
Water Absorption			ISO 62
Saturated, 23°C	0.80	%	ISO 62
Equilibrium, 23°C, 50% RH	0.20	%	ISO 62
Hardness	Nominal Value	Unit	Test Method
Ball Indentation Hardness (H 358/30)	110	MPa	ISO 2039-1
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	2000	MPa	ISO 527-2

Tensile Stress (Yield)	50.0	MPa	ISO 527-2/50
Tensile Strain (Yield)	12	%	ISO 527-2/50
Nominal Tensile Strain at Break	45	%	ISO 527-2/50
Tensile Creep Modulus ¹ (1000 hr)	1050	MPa	ISO 899-1
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179/1eA
-30°C	6.5	kJ/m ²	ISO 179/1eA
23°C	11	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength			ISO 179/1eU
-30°C	230	kJ/m ²	ISO 179/1eU
23°C	No Break		ISO 179/1eU
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	85.0	°C	ISO 75-2/A
Melting Temperature	167	°C	ISO 11357-3
CLTE - Flow (23 to 55°C)	1.3E-4	cm/cm/°C	ISO 11359-2
Maximum operating temperature-short cycle operation	100	°C	
Automotive Materials (> 1.00 mm)	Pass		FMVSS 302
ISO Type	POM-K, M-GNPR, 03-001		ISO 9988-1
Screw Speed		mm/sec	
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+14	ohms	IEC 60093
Volume Resistivity	1.0E+14	ohms · cm	IEC 60093
Dielectric Strength	85	kV/mm	IEC 60243-1
Relative Permittivity (1 MHz)	4.00		IEC 60250
Dissipation Factor (1 MHz)	0.014		IEC 60250
Comparative Tracking Index (Solution A)	600	V	IEC 60112
Flammability	Nominal Value	Unit	Test Method
Flame Rating (1.60 mm)	HB		UL 94
Injection	Nominal Value	Unit	
Drying Temperature	100	°C	
Drying Time	3.0	hr	
Suggested Max Moisture	0.20	%	
Hopper Temperature	200	°C	
Rear Temperature	200	°C	
Middle Temperature	200	°C	
Front Temperature	200	°C	
Nozzle Temperature	200	°C	
Processing (Melt) Temp	190 - 215	°C	
Mold Temperature	60.0 - 80.0	°C	
Injection instructions			
Residence Time: <10 min.			

NOTE

1. strain $\leq 0,5\%$, 23°C

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

