

Laser+® HS Ti818 (G51A)

Polyethylene Terephthalate

DAK Americas LLC

Message:

Laser+ ® HS Ti818 (G51A) is a Polyethylene Terephthalate (PET) material. It is available in Latin America or North America for injection stretch blow molding.

Important attributes of Laser+ ® HS Ti818 (G51A) are:

- Copolymer
- Eco-Friendly/Green
- Food Contact Acceptable

Typical applications include:

- Containers
- Food Contact Applications
- Packaging

General Information			
Features	Antimony Free		
	Copolymer		
	Food Contact Acceptable		
	Recyclable Material		
Uses	Containers		
	Packaging		
Agency Ratings	FDA FCN 85		
Forms	Pellets		
Processing Method	Injection Stretch Blow Molding		
Physical	Nominal Value	Unit	Test Method
Bulk Density	897	kg/m ³	Internal Method
Acetaldehyde	< 2.0	ppm	Internal Method
Color			Internal Method
CIE b*	-5.0 to -1.0		
CIE L*	76 to 80		
Crystallinity	> 45	%	Internal Method
Intrinsic Viscosity	0.77 to 0.81	dl/g	Internal Method
Moisture Content - as packaged	< 0.25	wt%	Internal Method
Particle Size - Shape (Cylindrical)	3x2x2	mm	Internal Method
Chip Size - nominal	59.0	count/g	Internal Method
Fines - as packaged, +24 Mesh Size	< 0.1	wt%	Internal Method
Thermal	Nominal Value	Unit	Test Method
Melting Temperature	240	°C	Internal Method
Injection	Nominal Value	Unit	Test Method
Drying Temperature	149 to 171	°C	

Drying Time	4.0 to 6.0	hr
Dew Point	< -36.7	°C

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

