

RX® 525

Phenolic

Sumitomo Bakelite North America, Inc.

Message:

RX525 is a cellulose fiber reinforced phenolic novolac molding compound. This material is recommended for parts requiring moderate toughness. It is designed to meet the requirements of ASTM D-5948-96, Type CFG.

General Information	
UL YellowCard	E123472-221457
Filler / Reinforcement	Cellulose
Features	Good Toughness
Agency Ratings	ASTM D 5948, Type CFG
Appearance	Black
Forms	Pellets
Processing Method	Compression Molding Injection Molding Resin Transfer Molding

Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.39	g/cm ³	ASTM D792
Apparent Density	0.50	g/cm ³	ASTM D1895
Molding Shrinkage - Flow (Compression Molded)	0.20	%	ASTM D955
Water Absorption (24 hr)	0.30	%	ASTM D570
Water Absorption - 48 hrs	1.7	%	ASTM D570
Flexural Strain at Break - Compression Molded	0.84	%	ASTM D790

Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (E-Scale, Compression Molded)	75		ASTM D785

Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Compression Molded)	41.0	MPa	ASTM D638
Flexural Modulus (Compression Molded)	8300	MPa	ASTM D790
Flexural Strength (Compression Molded)	69.0	MPa	ASTM D790
Compressive Strength	169	MPa	ASTM D695

Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (Compression Molded)	35	J/m	ASTM D256A

Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed, Compression Molded)	165	°C	ASTM D648
CLTE			ASTM E831

Flow	4.3E-5	cm/cm/°C	
Transverse	5.2E-5	cm/cm/°C	
Thermal Conductivity	0.54	W/m/K	ASTM C518
RTI Elec	150	°C	UL 746
RTI Imp	150	°C	UL 746
RTI Str	150	°C	UL 746
Electrical	Nominal Value	Unit	Test Method
Dielectric Strength ¹			ASTM D149
-- ²	2.0	kV/mm	
-- ³	1.0	kV/mm	
Arc Resistance	70.0	sec	ASTM D495
Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94
1.60 mm	HB		
3.20 mm	V-0		
NOTE			
1.	Wet, 60 Hz		
2.	Method A (Short-Time)		
3.	Method B (Step-by-Step)		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

