Wuxi Jiahong EB-2021

Polyvinyl Chloride

Wuxi Jiahong Plastics Technology CO., Ltd.

Message:

The products are used for round pipes, and IC electric packing pipes for production techniques of deformed moulds, as well as other round and deformed transparent pipes with various specifications. They possess fair surface polish, and SGS certificate for environment protection. Features of Product:

Applicable to extrusion; used for IC packing pipes or deformed transparent pipes; the products possess fair surface polish; the mold-cleaning cycle is long. Product Purpose:

High-speed granules for deformed or pipe-type molds, used for products with special transparency requirement.

| General Information | | | |
|-----------------------------|-------------------|-------|-----------------|
| Uses | Piping system | | |
| Appearance | Light Blue | | |
| | Clear/transparent | | |
| | | | |
| Forms | Particles | | |
| Processing Method | Extrusion | | |
| Physical | Nominal Value | Unit | Test Method |
| Specific Gravity | 1.25 - 1.35 | g/cm³ | Internal method |
| Vinyl Content | | ppm | GB/T 5009 |
| Volatile Matter | | % | GB/T 2918 |
| Mechanical | Nominal Value | Unit | Test Method |
| Tensile Strength | > 45.0 | MPa | Internal method |
| Thermal | Nominal Value | Unit | Test Method |
| Vicat Softening Temperature | > 70.0 | °C | GB/T 1633 |
| Optical | Nominal Value | Unit | Test Method |
| Transmittance | > 85.0 | % | Internal method |
| Haze | < 4.0 | % | Internal method |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd. Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

