

Leona™ FR200

Polyamide 66

Asahi Kasei Chemicals Corporation

Message:

Leona™ FR200 is a Polyamide 66 (Nylon 66) product. It is available in Africa & Middle East, Asia Pacific, Europe, or North America. Typical application: Electrical/Electronic Applications.
Characteristics include:
Flame Rated
Flame Retardant
Halogen Free

General Information	
UL YellowCard	E48285-240914
Additive	Flame Retardant
Features	Flame Retardant
	Halogen Free
Uses	Connectors
	Electrical Parts
	Electrical/Electronic Applications
	Switches

Physical	Dry	Conditioned	Unit	Test Method
Specific Gravity	1.16	--	g/cm ³	ASTM D792, ISO 1183
Molding Shrinkage - Flow	1.3 to 2.0	--	%	Internal Method
Water Absorption				
Saturation, 23°C	--	2.4	%	
Equilibrium, 23°C, 50% RH	--	2.4	%	ISO 62
Hardness	Dry	Conditioned	Unit	Test Method
Rockwell Hardness				ASTM D785, ISO 2039-2
M-Scale	80	--		
R-Scale	118	90		
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus (23°C)	3500	1100	MPa	ISO 527-2
Tensile Stress				
Yield, 23°C	75.0	44.0	MPa	ISO 527-2
Break, 23°C	69.0	--	MPa	ISO 527-2
--	79.0	47.0	MPa	ASTM D638
Tensile Strain				
Yield, 23°C	3.5	24	%	ISO 527-2
Break	25	80	%	ASTM D638

Break, 23°C	10	> 100	%	ISO 527-2
Flexural Modulus				
--	2900	1100	MPa	ASTM D790
23°C	2900	1000	MPa	ISO 178
Flexural Strength				
--	118	44.0	MPa	ASTM D790
23°C	117	37.2	MPa	ISO 178
Taber Abrasion Resistance (1000 Cycles)	--	8.00	mg	ASTM D1044
Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength	4.0	11	kJ/m ²	ISO 179
Charpy Unnotched Impact Strength	No Break	No Break		ISO 179
Notched Izod Impact	29	120	J/m	ASTM D256
Thermal	Dry	Conditioned	Unit	Test Method
Deflection Temperature Under Load				
0.45 MPa, Unannealed	209	--	°C	ASTM D648
0.45 MPa, Unannealed	203	--	°C	ISO 75-2/B
1.8 MPa, Unannealed	66.0	--	°C	ASTM D648
1.8 MPa, Unannealed	62.0	--	°C	ISO 75-2/A
CLTE - Flow	8.0E-5	--	cm/cm/°C	ASTM D696
Specific Heat	1670	--	J/kg/°C	
Thermal Conductivity	0.20	--	W/m/K	
Electrical	Dry	Conditioned	Unit	Test Method
Surface Resistivity	1.0E+13	--	ohms	ASTM D257, IEC 60093
Volume Resistivity				
--	1.0E+14	--	ohms·cm	ASTM D257
23°C	1.0E+14	--	ohms·cm	IEC 60093
Dielectric Strength	19	--	kV/mm	ASTM D149, IEC 60243-1
Comparative Tracking Index (3.00 mm)	600	--	V	IEC 60112
Flammability	Dry	Conditioned	Unit	Test Method
Flame Rating (0.750 mm)	V-0	--		UL 94
Glow Wire Flammability Index (3.00 mm)	960	--	°C	IEC 60695-2-12
Oxygen Index	32	--	%	ASTM D2863

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

