DJSilicone NE-7180

Silicone

DONGJUE SILICONE (NANJING) CO., LTD

Message:

Common silicone rubber for molding&extrusion has excellent high and low temperature resistance, electrical performance, and physical and mechanical properties. Despite of slightly worse transparency than general silicone rubber, it is more suitable for manufacturing colored products. There are two kinds of this product, namely modifying silicone rubber for molding and modifying silicone rubber for extrusion. The former can be vulcanized by DMDBH and used for manufacturing industrial accessories like keypad, seal ring and seal pad etc, while the latter can be vulcanized by DCBP and used for manufacturing wire, cable, rubber tube and rubber strip etc.

| General Information | | | |
|------------------------------|---------------------------|-------|-------------|
| Features | Good Colorability | | |
| | High Heat Resistance | | |
| | Low Temperature Resistant | | |
| Uses | Seals | | |
| Appearance | White | | |
| Processing Method | Injection Molding | | |
| Physical | Nominal Value | Unit | Test Method |
| Density | 1.20 to 1.30 | g/cm³ | ASTM D1505 |
| Hardness | Nominal Value | Unit | Test Method |
| Durometer Hardness (Shore A) | 77 to 83 | | ASTM D2240 |
| Elastomers | Nominal Value | Unit | Test Method |
| Tensile Set | < 6 | % | ASTM D412 |
| Tensile Strength (Yield) | > 7.00 | MPa | ASTM D412 |
| Tensile Elongation (Break) | > 150 | % | ASTM D412 |
| Tear Strength | > 16.0 | kN/m | ASTM D624 |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

