

# LACTEL® 85:15 DL-PLG

Polylactic Acid

DURECT Corporation

## Message:

DLG = poly(DL-lactide-co-glycolide)

Materials available:

B6006-1: Inherent Viscosity - 0.55 to 0.75 IV

This product is soluble in dichloromethane, tetrahydrofuran, ethyl acetate, chloroform, hexafluoroisopropanol, and acetone.

General Information		
Features	Amorphous	
	Biodegradable	
	Renewable Resource Content	
Forms	Pellets	
Physical	Nominal Value	Unit
Specific Gravity	1.27	g/cm <sup>3</sup>
Viscosity Number	55.0 to 75.0	cm <sup>3</sup> /g
Mechanical	Nominal Value	Unit
Tensile Modulus	1380 to 2760	MPa
Tensile Strength	41.4 to 55.2	MPa
Tensile Elongation (Break)	3.0 to 10	%
Thermal	Nominal Value	Unit
Glass Transition Temperature	50.0 to 55.0	°C
Additional Information	Nominal Value	Unit
Approx. Resorption	5.0 to 6.0	month
Crystalline Melt Transition	Amorphous	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

## Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT