

Kazan LLDPE PE2NT06-6

Linear Low Density Polyethylene

Kazanorgsintez Joint Stock Company

Message:

The intention of PE2NT06-6 LLDPE grade is to be processed into high-strength film.

General Information		
Features	High Tensile Strength	
Uses	Film	
Forms	Pellets	
Physical	Nominal Value	Unit
Density	0.916 to 0.920	g/cm ³
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	3.2 to 3.7	g/10 min
Ash Content	< 0.050	%
Melt Flow	< 10	%
Volatiles	< 0.090	%

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

