

XIRAN® SG260

Styrene Maleic Anhydride

Polyscope Polymers BV

Message:

XIRAN® SG260 are SMA (styrene maleic anhydride) based injection molding compounds with:

high thermal stability

high dimensional stability

excellent surface adhesion properties

Application areas

XIRAN® SG260 is a 30% glass filled injection molding compound designed for applications with high stiffness-strength. These products are very suitable for painted and foamed parts, high temperature resistance and precision parts with high shot to shot consistency.

| General Information | |
|------------------------|----------------------------------|
| Filler / Reinforcement | Glass Fiber,30% Filler by Weight |
| Features | Foamable |
| | Good Adhesion |
| | Good Dimensional Stability |
| | Good Thermal Stability |
| | High Stiffness |
| | High Strength |
| | Paintable |
| Uses | Foam |
| | High Temperature Applications |
| Forms | Granules |
| Processing Method | Compounding |
| | Injection Molding |

| Physical | Nominal Value | Unit | Test Method |
|--|---------------|-------------------|-----------------|
| Density | 1.28 | g/cm ³ | ISO 1183 |
| Melt Mass-Flow Rate (MFR) (220°C/10.0 kg) | 2.5 | g/10 min | ISO 1133 |
| Spiral Flow ¹ | 26.0 | cm | Internal Method |
| Molding Shrinkage ² | | | Internal Method |
| Across Flow | 0.50 | % | |
| Flow | 0.20 | % | |
| Water Absorption (Equilibrium, 23°C, 50% RH) | 0.20 | % | ASTM D570 |
| Mechanical | Nominal Value | Unit | Test Method |
| Tensile Modulus | 8500 | MPa | ISO 527-2 |
| Tensile Stress (Break) | 90.0 | MPa | ISO 527-2 |
| Tensile Strain (Break) | 2.0 | % | ISO 527-2 |

| | | | |
|---|--|-------------------|-------------|
| Flexural Modulus | 8500 | MPa | ISO 178 |
| Flexural Stress | 150 | MPa | ISO 178 |
| Impact | Nominal Value | Unit | Test Method |
| Charpy Notched Impact Strength | | | ISO 179/1eA |
| -40°C | 8.0 | kJ/m ² | |
| 23°C | 9.0 | kJ/m ² | |
| Charpy Unnotched Impact Strength | | | ISO 179/1eU |
| -40°C | 34 | kJ/m ² | |
| 23°C | 30 | kJ/m ² | |
| Notched Izod Impact Strength | | | ISO 180/A |
| -40°C | 8.0 | kJ/m ² | |
| 23°C | 9.0 | kJ/m ² | |
| Thermal | Nominal Value | Unit | Test Method |
| Heat Deflection Temperature (1.8 MPa, Unannealed) | 120 | °C | ISO 75-2/A |
| Vicat Softening Temperature | 118 | °C | ISO 306/B |
| CLTE | | | ASTM D696 |
| Flow : -30 to 80°C | 2.9E-5 | cm/cm/°C | |
| Transverse : -30 to 80°C | 4.7E-5 | cm/cm/°C | |
| Flammability | Nominal Value | | Test Method |
| Flame Rating | HB | | UL 94 |
| Injection | Nominal Value | Unit | |
| Drying Temperature | 80.0 to 90.0 | °C | |
| Drying Time | 2.0 to 3.0 | hr | |
| Rear Temperature | 230 to 250 | °C | |
| Middle Temperature | 230 to 250 | °C | |
| Front Temperature | 230 to 250 | °C | |
| Nozzle Temperature | 245 to 275 | °C | |
| Processing (Melt) Temp | < 285 | °C | |
| NOTE | | | |
| 1. | 2 mm | | |
| 2. | Measured according to the Autodesk Mold flow Plastics Labs using a tag mold. | | |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

