

Durethan® BKV 140 DUS008 000000

Polyamide 6

LANXESS GmbH

Message:

PA 6, 40 % glass fibers, injection molding, improved impact strength

General Information			
Filler / Reinforcement	Glass fiber reinforced material, 40% filler by weight		
Features	Impact resistance, good		
Agency Ratings	EC 1907/2006 (REACH)		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Molding Shrinkage			ISO 2577
Vertical flow direction: 280°C, 2.00mm ¹	0.75	%	ISO 2577
Vertical flow direction: 120°C, 4 hours, 2.00mm ²	0.090	%	ISO 2577
Flow direction: 280°C, 2.00mm ³	0.21	%	ISO 2577
Flow direction: 120°C, 4 hours, 2.00mm ⁴	0.070	%	ISO 2577
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus (23°C)	12000	MPa	ISO 527-2/1
Tensile Stress (Break, 23°C)	185	MPa	ISO 527-2/5
Tensile Strain (Break, 23°C)	3.4	%	ISO 527-2/5
Flexural Modulus ⁵ (23°C)	11000	MPa	ISO 178/A
Flexural Stress			ISO 178/A
3.5% strain, 23°C	280	MPa	ISO 178/A
23°C ⁶	290	MPa	ISO 178/A
Flexural Strain at Flexural Strength ⁷ (23°C)	4.2	%	ISO 178/A
ISO Shortname	PA 6HI, GR, 14-120, GF40		ISO 1874
Residual Moisture Content	0.030 - 0.12	%	Karl Fisher
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179/1eA
-30°C	10	kJ/m ²	ISO 179/1eA
23°C	15	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength			ISO 179/1eU
-30°C	100	kJ/m ²	ISO 179/1eU
23°C	110	kJ/m ²	ISO 179/1eU
Notched Izod Impact (23°C)	11	kJ/m ²	ISO 180/1A
Unnotched Izod Impact Strength			ISO 180/1U
-30°C	90	kJ/m ²	ISO 180/1U
23°C	90	kJ/m ²	ISO 180/1U

Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, not annealed	217	°C	ISO 75-2/B
1.8 MPa, not annealed	201	°C	ISO 75-2/A
Melting Temperature ⁸	220	°C	ISO 11357-3
Injection	Nominal Value	Unit	Test Method
Drying Temperature - Dry Air Dryer	80.0	°C	
Drying Time - Dry Air Dryer	2.0 - 6.0	hr	
Processing (Melt) Temp	260 - 290	°C	
Mold Temperature	80.0 - 100	°C	
NOTE			
1.	60x60x2mm, 80°C MT, 400 bar		
2.	60x60x2mm		
3.	60x60x2mm, 80°C MT, 400 bar		
4.	60x60x2mm		
5.	2.0 mm/min		
6.	2.0 mm/min		
7.	2 mm/min		
8.	10°C/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

