

Sumiliteresin® PR-NR-1

Phenolic
SBHPP

Message:

Cashew modified phenolic resin
High Modulus
Low Tangent delta

General Information		
Thermal	Nominal Value	Unit
Softening Point - B&R;	94	°C
Free Phenol - GC	1.0	%

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

