Styropek® BF 295M

Expanded Polystyrene

Styropek S.A. de C.V.

Message:

Styropek® BF products can be used in a wide variety of applications including blocks for construction, panels, thermal and acoustical insulation, and general packaging. Additional applications include ICF's ("insulated concrete forms"), thin walled custom molding, lost foam and other general protective packaging.

Modified expandable polystyrene (EPS) / non-flammable / antiflame / auto-extinguishable that containing approximately 5.5 to 6.4 wt% pentane as blowing agent.

All products are supplied as spherical beads with a bulk density of approximately 40 lb/ft3 (640 kg/m3).

Styropek® BF products are compatible with many anti-stat, mineral oil, color additives and other additives added during processing.

Styropek® BF products do not contain chlorofluorocarbons and hydrofluorocarbons compounds.

Intended uses

Block molding applications, low-range densities, thickness of wall >12 cm, with excellent fusion and high regrind addition.

| General Information | | | |
|-----------------------------|---------------------------------|-------|--|
| UL YellowCard | E474710-102172942 | | |
| Additive | Foaming agent (6%) 3 | | |
| Features | Recyclable materials | | |
| | Can foam | | |
| | Self-extinguishing | | |
| | Flame retardancy | | |
| | | | |
| Uses | Packaging | | |
| | Building materials | | |
| | Architectural application field | | |
| | Insulating material | | |
| | Foam | | |
| | | | |
| Agency Ratings | ASTM C 578 | | |
| | ASTM E 84 | | |
| | EC 1907/2006 (REACH) | | |
| | | | |
| RoHS Compliance | RoHS compliance | | |
| Forms | Sphere | | |
| Physical | Nominal Value | Unit | |
| Apparent Density | 0.64 | g/cm³ | |
| Additional Information | Nominal Value | Unit | |
| Bead Size (0.850 to 1.70mm) | > 97 | % | |
| Expanded Density | 9.50 - 19.0 | kg/m³ | |
| Monomer Residue | | ppm | |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



Page 2