

# Formolene® 6730L

Polypropylene Copolymer

Formosa Plastics Corporation, U.S.A.

## Message:

Formolene® 6730L is a high melt flow copolymer polypropylene designed for injection and compounding applications.

General Information			
Features	Copolymer		
Agency Ratings	EC 1907/2006 (REACH)		
Processing Method	Composite		
	Injection molding		
Physical	Nominal Value	Unit	Test Method
Density	0.900	g/cm <sup>3</sup>	ASTM D1505
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	33	g/10 min	ASTM D1238
Mechanical	Nominal Value	Unit	Test Method
Flexural Modulus - 1% Secant <sup>1</sup> (Injection Molded)	966	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, Injection Molded)	160	J/m	ASTM D256A
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, unannealed, injection molded	97.0	°C	ASTM D648
1.8 MPa, unannealed, injection molded	51.0	°C	ASTM D648
NOTE			
1.	1.3 mm/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

## Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT