

Clariant PC PC-020-L

Polycarbonate
Clariant Corporation

Message:

Clariant PC PC-020-L is a Polycarbonate (PC) material filled with 20% glass fiber. It is available in North America for injection molding.

Important attributes of Clariant PC PC-020-L are:

Good Stiffness
Lubricated

General Information			
UL YellowCard	E103015-218204		
Filler / Reinforcement	Glass Fiber,20% Filler by Weight		
Additive	Lubricant		
Features	Good Stiffness		
	Lubricated		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.36	g/cm³	ASTM D792
Molding Shrinkage - Flow	0.40	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	82.7	MPa	ASTM D638
Tensile Elongation (Break)	4.0	%	ASTM D638
Flexural Modulus	5170	MPa	ASTM D790
Flexural Strength	131	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	75	J/m	ASTM D256
Tensile Impact Strength	94.6	kJ/m²	ASTM D1822
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed	141	°C	
1.8 MPa, Unannealed	138	°C	
Melting Temperature	257	°C	
Injection	Nominal Value	Unit	
Drying Temperature	121	°C	
Drying Time	3.0 to 4.0	hr	
Suggested Max Regrind	20	%	
Rear Temperature	288 to 304	°C	
Middle Temperature	299 to 316	°C	
Front Temperature	304 to 338	°C	

Nozzle Temperature	304 to 338	°C
Processing (Melt) Temp	288 to 299	°C
Mold Temperature	82.2 to 116	°C
Injection Pressure	110 to 138	MPa
Back Pressure	0.345 to 1.38	MPa
Screw Speed	60 to 80	rpm

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

