

RTP 1002 HI FR A

Polybutylene Terephthalate

RTP Company

Message:

Warning: The status of this material is 'Commercial: Limited Issue'
The data for this material has not been recently verified.
Please contact RTP Company for current information prior to specifying this grade.

General Information			
Filler / Reinforcement	Glass fiber reinforced material, 15% filler by weight		
Features	Impact resistance, high		
	Flame retardancy		
RoHS Compliance	Contact manufacturer		
Appearance	Black		
	Natural color		
Forms	Particle		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.46	g/cm³	ASTM D792
Molding Shrinkage - Flow (3.18 mm, Injection Molded)	0.40	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus (Injection Molded)	4130	MPa	ASTM D638
Tensile Strength	61.0	MPa	ASTM D638
Tensile Elongation (Yield, Injection Molded)	7.0	%	ASTM D638
Flexural Modulus (Injection Molded)	3450	MPa	ASTM D790
Flexural Strength (Injection Molded)	96.0	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (3.18 mm, Injection Molded)	140	J/m	ASTM D256
Unnotched Izod Impact (3.18 mm)	800	J/m	ASTM D4812
Flammability	Nominal Value		Test Method
Flame Rating (1.50 mm)	V-0		UL 94
Additional Information			
The value listed as Flammibility, UL 94, was tested in accordance with RTP Company methods.			
Injection	Nominal Value	Unit	
Rear Temperature	232 - 257	°C	
Middle Temperature	232 - 257	°C	
Front Temperature	232 - 257	°C	

Mold Temperature	79.0 - 107	°C
Injection Pressure	69.0 - 103	MPa

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

