

# Aurora PVC AP3141 Series

Rigid Polyvinyl Chloride

Aurora Plastics, Inc.

## Message:

A rigid PVC powder compound for the extrusion of a medium density foam.

General Information			
Features	Foamable High Rigidity Medium Density		
Uses	Foam		
Forms	Powder		
Processing Method	Foam Extrusion		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.748 to 0.848	g/cm <sup>3</sup>	ASTM D792
Water Absorption (Saturation)	0.80	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus (22°C)	1100	MPa	ASTM D638
Tensile Strength (Yield, 22°C)	17.9	MPa	ASTM D638
Flexural Modulus (22°C)	1280	MPa	ASTM D790
Flexural Strength (22°C)	37.9	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (22°C)	21	J/m	ASTM D256
Drop Impact Resistance <sup>1</sup> (22°C, Extruded at 370 to 380° F melt temperature)	8.01	J/cm	ASTM D4226
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	65.6	°C	ASTM D648
CLTE - Flow (22°C)	5.4E-5	cm/cm/°C	ASTM D696
Flammability	Nominal Value		Test Method
Flame Rating	HB		ASTM D635
NOTE			
1.	Procedure B		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

