

Indothene HD 52GB003

High Density Polyethylene

Reliance Industries Limited

Message:

Indothene-HD 52GB003 is a High Molecular Weight High Density Polyethylene blow molding grade with high stiffness and impact strength and good ESCR produced by Stirred Tank Heavy Diluent (STHD) process adopting process know-how of M/s. Basell, Germany. It possesses medium molecular weight distribution, very good swell and easy processability. Indothene-HD 52GB003 can readily be processed on most HDPE blow moulding machines. FOOD CONTACT APPLICATIONS :

This grade meets the requirements of Indian Standard IS-10146-1982 on "Polyethylene for its safe use in contact with food stuffs, pharmaceuticals and drinking water". It also conforms to the positive list of constituents as approved in IS:10141:1982. The grade complies with FDA regulation : CFR title 21 , 177.1520, Olefin polymer

General Information			
Features	Food Contact Acceptable		
	Good Processability		
	High ESCR (Stress Crack Resist.)		
	High Impact Resistance		
	High Molecular Weight		
	High Stiffness		
	Med.-Wide Molecular Weight Distrib.		
Uses	Blow Molding Applications		
	Containers		
	Drums		
	Food Containers		
Agency Ratings	FDA 21 CFR 177.1520		
Appearance	Natural Color		
Forms	Pellets		
Processing Method	Blow Molding		
Physical	Nominal Value	Unit	Test Method
Density	0.952	g/cm ³	ASTM D1505
Melt Mass-Flow Rate (MFR)			ASTM D1238
190°C/21.6 kg	8.5	g/10 min	
190°C/5.0 kg	0.45	g/10 min	
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength ¹ (Yield, 3.20 mm, Injection Molded)	29.0	MPa	ASTM D638
Tensile Elongation ² (Yield, 3.20 mm, Injection Molded)	11	%	ASTM D638
Flexural Modulus ³ (3.20 mm, Injection Molded)	1000	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method

Notched Izod Impact (3.20 mm, Injection Molded)	No Break	ASTM D256	
Thermal	Nominal Value	Unit	Test Method
Vicat Softening Temperature	125	°C	ASTM D1525
Extrusion	Nominal Value	Unit	
Cylinder Zone 1 Temp.	180	°C	
Cylinder Zone 2 Temp.	190	°C	
Cylinder Zone 3 Temp.	200	°C	
Cylinder Zone 4 Temp.	210	°C	
Die Temperature	205	°C	
NOTE			
1.	Type I		
2.	Type I		
3.	Type I		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

