POLIMAXX GP110

General Purpose Polystyrene

IRPC Public Company Limited

Message:

GP110 is a general purpose grade of polystyrene resin for extrusion process and injection process with high strength and good clarity. It is suitable for food packaging (XPS), electrical appliances (refrigerator food tray), household products, sanitary ware and etc. It also meets the requirement of food contact regulation.

General Information			
UL YellowCard	E132283-222119		
Features	Food Contact Acceptable		
	General Purpose		
	High Strength		
	Medium Clarity		
Uses	Appliance Components		
	Electrical/Electronic Applications		
	Food Packaging		
	General Purpose		
	Household Goods		
RoHS Compliance	RoHS Compliant		
Processing Method	Extrusion		
	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Melt Mass-Flow Rate (MFR) (200°C/5.0 kg)	1.7	g/10 min	ASTM D1238
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (M-Scale, 23°C, 6.35	90		ASTM D785
mm) Mechanical	80 Nominal Value	Unit	Test Method
	52.4	MPa	ASTM D638
Tensile Strength (Yield, 23°C) Flexural Modulus (23°C)	3240	MPa	ASTM D050
Flexural Modulus (23°C)			ASTM D790
Thermal	99.9 Nominal Value	MPa Unit	Test Method
	Nominal value	Unit	
Deflection Temperature Under Load (1.8 MPa, Unannealed, 6.35 mm)	98.0	°C	ASTM D648
Vicat Softening Temperature	107	°C	ASTM D1525
Flammability	Nominal Value		Test Method
Flame Rating (3.00 mm)	НВ		UL 94
Injection	Nominal Value	Unit	

Processing	(Melt)	Temp
------------	--------	------

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

