# MAJORIS DEG464X - 8432

### Polypropylene

#### AD majoris

#### Message:

MAJORIS DEG464X-8432 is a high performance reinforced polypropylene compound intended for injection moulding.

The product is available in natural, but other colours can be provided on request.

MAJORIS DEG464X-8432 has been developed especially for demanding applications in various engineering sectors.

MAJORIS DEG464X-8432 has high rigidity and impact strength, good dimensional stability, very good stiffness and good creep resistancy also at high temperatures.

**APPLICATIONS** 

Product requiring very high overall mechanical performance such as:

Electrical tool and appliance components

Under the bonnet parts

Miscellaneous technical items

General Information					
Features	Good dimensional stability				
	Rigidity, high				
	Rigid, good				
	Impact resistance, high				
	Recyclable materials				
	Good creep resistance				
Uses	Electrical/Electronic Applications				
	Power/other tools				
	Home appliance components				
	Parts under the hood of a car				
Appearance	Available colors				
	Natural color				
Forms	Particle				
Processing Method	Injection molding				
Physical	Nominal Value	Unit	Test Method		
Density	1.20	g/cm³	ISO 1183		
Melt Mass-Flow Rate (MFR) (230°C/2.16					
kg)	6.0	g/10 min	ISO 1133		
Molding Shrinkage			Internal method		
Vertical flow direction: 2.00mm	0.70	%	Internal method		
Flow direction: 2.00mm	0.30	%	Internal method		
Mechanical	Nominal Value	Unit	Test Method		
Tensile Modulus	6550	MPa	ISO 527-2/1		
Tensile Stress (Yield)	80.0	MPa	ISO 527-2/50		

Tensile Strain (Break)	4.2	%	ISO 527-2/50	
Flexural Modulus <sup>1</sup>	6800	MPa	ISO 178	
Flexural Stress	140	MPa	ISO 178	
Impact	Nominal Value	Unit	Test Method	
Charpy Notched Impact Strength (23°C)	16	kJ/m²	ISO 179/1eA	
Charpy Unnotched Impact Strength (23°C)	55	kJ/m²	ISO 179/1eU	
Injection	Nominal Value	Unit		
Processing (Melt) Temp	230 - 270	°C		
Mold Temperature	30.0 - 60.0	°C		
Injection Rate	Moderate			
Holding Pressure	30.0 - 60.0	MPa		
Injection instructions				
Screw speed: Low to mediumBack pressure: Low to medium				
NOTE				
1.	2.0 mm/min			

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

