

Next Nylon 6 Prime Series NGM30-01GY

Polyamide 6

Next Polymers Ltd.

Message:

Description

PA6 Glass/Mineral Fiber Reinforced Grey compound

Product Applications

This grade is commonly used in the Automotive industry to mold a large part with a low warpage Such as Fan blades, engine cover, Heater grill, car body parts, housing.

Benefits

This grade offers an excellent planarity of the end product, High mechanical property with a high dimensional stability.

General Information				
Filler / Reinforcement	Glass\Mineral,30% Filler by Weight			
Features	Good Dimensional Stability			
	Low Warpage			
Uses	Automotive Applications			
	Housings			
Agency Ratings	EC 1907/2006 (REACH)			
RoHS Compliance	RoHS Compliant			
Appearance	Grey			
Processing Method	Injection Molding			
Physical	Dry	Conditioned	Unit	Test Method
Specific Gravity	1.37	--	g/cm ³	ASTM D792
Molding Shrinkage				ASTM D955
Flow	0.30	--	%	
Across Flow	0.85	--	%	
Water Absorption				ASTM D570
23°C, 24 hr	1.9	--	%	
Saturation ¹	6.2	--	%	
Hardness	Dry	Conditioned	Unit	Test Method
Rockwell Hardness				ASTM D785
M-Scale	105	--		
R-Scale	115	--		
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Strength	100	55.0	MPa	ASTM D638
Tensile Elongation (Break)	4.0	12	%	ASTM D638
Flexural Modulus	6200	--	MPa	ASTM D790
Flexural Strength	140	--	MPa	ASTM D790
Impact	Dry	Conditioned	Unit	Test Method

Notched Izod Impact (23°C)	59	78	J/m	ASTM D256
Thermal	Dry	Conditioned	Unit	Test Method
Deflection Temperature Under Load				ASTM D648
0.45 MPa, Unannealed	205	--	°C	
1.8 MPa, Unannealed	180	--	°C	
Melting Temperature	220	--	°C	ASTM D2117
Electrical	Dry	Conditioned	Unit	Test Method
Surface Resistivity	--	1.0E+13	ohms	IEC 60093
Volume Resistivity	1.0E+14	1.0E+12	ohms·cm	IEC 60093
Electric Strength	32	30	kV/mm	IEC 60243-1
Comparative Tracking Index	--	500	V	IEC 60112
Flammability	Dry	Conditioned	Unit	Test Method
Flame Rating (0.800 mm)	HB	--		UL 94
Injection	Dry	Unit		
Drying Temperature - Hot Air Dryer	80.0		°C	
Drying Time	4.0 to 6.0		hr	
Suggested Max Moisture	0.20		%	
Rear Temperature	230 to 240		°C	
Middle Temperature	240 to 250		°C	
Front Temperature	250 to 260		°C	
Mold Temperature	80.0 to 100		°C	
NOTE				

1. Immersed

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT