Paracril® B

Acrylonitrile Butadiene Rubber

INSA

Message:

Description: Excellent low temperature flexibility with oil resistance. High green strength. Hot polymerized. Non staining stabilizer. Applications: Automotive products, seals, hoses, o-rings and packings. Adhesives. Sponge. Coated fabrics Roll covers.

| General Information | | | |
|----------------------------------|-----------------------------|-------|-------------|
| Features | Good Green Strength | | |
| | Low Temperature Flexibility | | |
| | Oil Resistant | | |
| | Stain Resistant | | |
| | | | |
| Uses | Adhesives | | |
| | Automotive Applications | | |
| | Coating Applications | | |
| | Fabric Coatings | | |
| | Seals | | |
| | Tubing | | |
| | | | |
| Physical | Nominal Value | Unit | Test Method |
| Specific Gravity | 0.970 | g/cm³ | ASTM D297 |
| Mooney Viscosity (ML 1+4, 100°C) | 78 to 92 | MU | ASTM D1646 |
| ACN Contout Down d | 20.0 1 21.0 | 10/ | |

| Mooney Viscosity (ML 1+4, 100°C) | 78 to 92 | MU | ASTM D1646 |
|----------------------------------|--------------|-----|-----------------|
| ACN Content - Bound | 28.0 to 31.0 | wt% | Internal Method |
| Ash Content | < 0.8 | wt% | ASTM D5667 |
| Volatile Matter | < 1.0 | wt% | ASTM D5668 |
| | | | |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519 Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

