

Durethan® BKV 60 EF DUS097 000000

Polyamide 6

LANXESS Asia/Pacific

Message:

PA 6, 60 % glass fibers, injection molding, improved flowability, heat-aging stabilized

General Information				
Filler / Reinforcement	Glass Fiber,60% Filler by Weight			
Additive	Heat Stabilizer			
Features	Good Flow			
	Heat Stabilized			
Agency Ratings	EC 1907/2006 (REACH)			
Processing Method	Injection Molding			
Physical	Dry	Conditioned	Unit	Test Method
Molding Shrinkage				ISO 2577
Across Flow : 280°C, 2.00 mm ¹	0.60	--	%	
Across Flow : 120°C, 4 hr, 2.00 mm ²	0.020	--	%	
Flow : 280°C, 2.00 mm ³	0.30	--	%	
Flow : 120°C, 4 hr, 2.00 mm ⁴	0.030	--	%	
Water Absorption				ISO 62
Saturation, 23°C	3.8	--	%	
Equilibrium, 23°C, 50% RH	1.2	--	%	
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus (23°C)	19400	12500	MPa	ISO 527-2/1
Tensile Stress (Break, 23°C)	230	158	MPa	ISO 527-2/5
Tensile Strain (Break, 23°C)	2.5	3.5	%	ISO 527-2/5
Flexural Modulus ⁵ (23°C)	20000	13600	MPa	ISO 178/A
Flexural Stress				ISO 178/A
3.5% Strain,23°C	--	250	MPa	
23°C ⁶	390	260	MPa	
Flexural Strain at Flexural Strength ⁷ (23°C)	3.0	4.0	%	ISO 178/A
ISO Shortname	PA 6, GHR, 10-190, GF60	--		ISO 1874
Residual Moisture Content	0.060 to 0.20		%	Karl Fisher
Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength				ISO 179/1eA

-30°C	17	--	kJ/m ²	
23°C	17	24	kJ/m ²	
Charpy Unnotched Impact Strength (23°C)	95	95	kJ/m ²	ISO 179/1eU
Notched Izod Impact Strength				ISO 180/1A
-30°C	18	--	kJ/m ²	
23°C	18	29	kJ/m ²	
Unnotched Izod Impact Strength				ISO 180/1U
-30°C	95	95	kJ/m ²	
23°C	90	90	kJ/m ²	
Multi-Axial Instrumented Impact Energy				ISO 6603-2
-30°C	3.80	--	J	
23°C	4.30	--	J	
Multi-Axial Instrumented Impact Peak Force				ISO 6603-2
-30°C	1350	--	N	
23°C	1480	--	N	
Thermal	Dry	Conditioned	Unit	Test Method
Heat Deflection Temperature				
0.45 MPa, Unannealed	220	--	°C	ISO 75-2/B
1.8 MPa, Unannealed	213	--	°C	ISO 75-2/A
8.0 MPa, Unannealed	186	--	°C	ISO 75-2/C
Melting Temperature ⁸	221	--	°C	ISO 11357-3
CLTE				ISO 11359-2
Flow : 23 to 55°C	1.0E-5	--	cm/cm/°C	
Transverse : 23 to 55°C	8.0E-5	--	cm/cm/°C	
Injection	Dry	Unit	Test Method	
Drying Temperature - Dry Air Dryer	80.0		°C	
Drying Time - Dry Air Dryer	2.0 to 6.0		hr	
Processing (Melt) Temp	270 to 290		°C	
Mold Temperature	80.0 to 120		°C	
NOTE				
1.	60x60x2mm, 80°C MT, 600 bar			
2.	60x60x2mm			
3.	60x60x2mm, 80°C MT, 600 bar			
4.	60x60x2mm			
5.	2.0 mm/min			
6.	2.0 mm/min			

7.	2 mm/min
8.	10°C/min

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

