ALTECH® PA6 A 3030/500 GB30

Polyamide 6

ALBIS PLASTIC GmbH

Message:

ALTECH®PA6 A 3030/500 GB30 is a polyamide 6 (nylon 6) product containing 30% glass beads. It can be processed by injection molding and is available in North America, Europe or the Asia-Pacific region. Typical application areas are: housing. Features include: Comply with REACH standard ROHS certification high liquidity anti-warping heat stabilizer

General Information			
Filler / Reinforcement	Glass beads, 30% filler by weight		
Additive	heat stabilizer		
Features	Low warpage		
	High liquidity		
	Thermal Stability		
	Good demoulding performance		
Uses	Shell		
Agency Ratings	EC 1907/2006 (REACH)		
RoHS Compliance	RoHS compliance		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Density	1.36	g/cm³	ISO 1183
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	4200	MPa	ISO 527-2
Tensile Stress	60.0	MPa	ISO 527-2
Flexural Modulus	4000	MPa	ISO 178
Flexural Stress	100	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength	4.0	kJ/m²	ISO 179/1eA
Charpy Unnotched Impact Strength	40	kJ/m²	ISO 179/1eU
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (1.8 MPa,			
Unannealed)	75.0	°C	ISO 75-2/A
Vicat Softening Temperature	200	°C	ISO 306/B50
Injection	Nominal Value	Unit	
Drying Temperature - Desiccant Dryer	80	°C	
Drying Time - Desiccant Dryer	2.0 - 12	hr	
Suggested Max Moisture	0.015	%	

Processing (Melt) Temp	270 - 290	°C
Mold Temperature	80 - 100	°C

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

