Hanwha Total PP HY301

Polypropylene Homopolymer

HANWHA TOTAL PETROCHEMICALS Co., Ltd.

Message:

HY301 is a PP homopolymer for stretched tapes applications. This grade is suitable for laminating applications such as packaging films, injection-modeled housewares and woven bags.

General Information				
Features	Good Processability			
	Good Stretchability			
	High Tensile Strength			
	Homopolymer			
Uses	Bags			
	Containers			
	Film			
	Fishing Applications			
	Household Goods			
	Laminates			
	Netting			
	Packaging			
	Таре			
Forms	Pellets			
Processing Method	Extrusion			
	Injection Molding			
Physical	Nominal Value	Unit	Test Method	
Density	0.910	g/cm³	ASTM D1505	
Melt Mass-Flow Rate (MFR) (230°C/2.16	2.2			
kg)	3.3	g/10 min	ASTM D1238	
Hardness	Nominal Value	Unit	Test Method	
Rockwell Hardness (R-Scale)	100		ASTM D785	
Mechanical	Nominal Value	Unit	Test Method	
Tensile Strength	37.3	MPa	ASTM D638	
Tensile Elongation (Break)	500	%	ASTM D638	
Flexural Modulus	1570	MPa	ASTM D790	
Impact	Nominal Value	Unit	Test Method	
Notched Izod Impact	39	J/m	ASTM D256	
Thermal	Nominal Value	Unit	Test Method	

Deflection Temperature Under Load (MPa, Unannealed)	0.45	°C	ASTM D648
Vicat Softening Temperature	155	°C	ASTM D1525
Extrusion	Nominal Value	Unit	
Cylinder Zone 1 Temp.	150 to 200	°C	
Cylinder Zone 2 Temp.	150 to 200	°C	
Cylinder Zone 3 Temp.	150 to 200	°C	
Cylinder Zone 4 Temp.	150 to 200	°C	
Cylinder Zone 5 Temp.	150 to 200	°C	
Adapter Temperature	180 to 220	°C	
Die Temperature	180 to 220	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

