

Delrin® FG500TL NC010

ACETAL RESIN

DuPont Performance Polymers

Message:

Teflon® Lubricated Medium Viscosity Acetal Homopolymer with Low Wear and Low Friction Developed for Food Contact Applications

General Information			
UL YellowCard	E41938-100907476		
Filler / Reinforcement	PTFE Micropowder, 1.5% Filler by Weight		
Additive	Lubricant		
	Mold Release		
Features	Lubricated		
Agency Ratings	UL Unspecified Rating		
Forms	Pellets		
Processing Method	Injection Molding		
Multi-Point Data	Isothermal Stress vs. Strain (ISO 11403-1)		
	Secant Modulus vs. Strain (ISO 11403-1)		
Part Marking Code (ISO 11469)	>POM-SD<		
Resin ID (ISO 1043)	POM-SD		
Physical	Nominal Value	Unit	Test Method
Density	1.43	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	14	g/10 min	ISO 1133
Melt Volume-Flow Rate (MVR) (190°C/2.16 kg)	12.0	cm ³ /10min	ISO 1133
Molding Shrinkage			ISO 294-4
Across Flow	1.7	%	
Flow	1.8	%	
Water Absorption			ISO 62
23°C, 24 hr, 2.00 mm	0.90	%	
Equilibrium, 23°C, 2.00 mm, 50% RH	0.17	%	
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	3300	MPa	ISO 527-2
Tensile Stress (Yield)	71.0	MPa	ISO 527-2
Tensile Strain (Yield)	13	%	ISO 527-2
Nominal Tensile Strain at Break	20	%	ISO 527-2
Flexural Modulus	3100	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179/1eA

-30°C	4.0	kJ/m ²	
23°C	5.0	kJ/m ²	
Charpy Unnotched Impact Strength			ISO 179/1eU
-30°C	160	kJ/m ²	
23°C	170	kJ/m ²	
Notched Izod Impact Strength			ISO 180/1A
-40°C	6.0	kJ/m ²	
23°C	6.0	kJ/m ²	
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, Unannealed	165	°C	ISO 75-2/B
1.8 MPa, Unannealed	103	°C	ISO 75-2/A
Melting Temperature ¹	178	°C	ISO 11357-3
CLTE			ISO 11359-2
Flow	1.0E-4	cm/cm/°C	
Transverse	1.0E-4	cm/cm/°C	
Flammability	Nominal Value		Test Method
Flammability Classification (1.50 mm)	HB		IEC 60695-11-10, -20
NOTE			
1.	10°C/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

