KetaSpire® KT-880UFP

Polyetheretherketone

Solvay Specialty Polymers

Message:

KetaSpire[®] KT-880UFP is the high flow grade of unreinforced polyetheretherketone (PEEK) supplied in a natural-colored, ultra-fine powder form. This ultra-fine PEEK powder is suitable for water borne coatings, electrostatically driven powder coatings, and resin pre-impregnation of continuous fiber composites. This ultra fine powder is produced to a median particle size D50 of about 10 micrometers.

KetaSpire [®] PEEK is produced to the highest industry standards and is characterized by a distinct combination of properties, which include excellent chemical resistance to acids, bases and a broad range of aggressive organic chemicals, best in class fatigue resistance, high thermal resistance, high purity and ease of melt processing.

These properties make KT-880UFP well-suited for applications in health care, transportation, electronics, chemical processing and other industrial uses. The resin is also available in a natural-colored pellet form under the grade name KT-880 NT for injection molding applications.

General Information					
Features	Good dimensional stability				
	Impact resistance, good				
	Good chemical resistance				
	Fatigue resistance				
	Heat resistance, high				
	ductility				
	Flame retardancy				
Uses	Electrical/Electronic Applications				
	Industrial application				
	Aerospace applications				
	Application in Automobile Field				
	Oil/Gas Supplies				
RoHS Compliance	Contact manufacturer				
Appearance	Natural color				
Forms	Powder				
Processing Method	Water-borne Coating				
	Electrostatic jet coating				
Physical	Nominal Value	Unit	Test Method		
Specific Gravity	1.30	g/cm³	ASTM D792		
Water Absorption (24 hr)	0.10	%	ASTM D570		
Particle Size					
D50	10.0	μm			
D90	15.0	μm			
D99	22.0	μm			
Mechanical	Nominal Value	Unit	Test Method		

Tensile Modulus	3650	MPa	ASTM D638
Tensile Strength	100	MPa	ASTM D638
Tensile Elongation			ASTM D638
Yield	5.2	%	ASTM D638
Fracture ¹	10 - 20	%	ASTM D638
Flexural Modulus	3790	MPa	ASTM D790
Flexural Strength	153	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	53	J/m	ASTM D256
Unnotched Izod Impact	No Break		ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1	.8		
MPa, Unannealed)	160	°C	ASTM D648
Glass Transition Temperature	147	°C	ASTM D3417
Melting Temperature	343	°C	ASTM D3417
CLTE - Flow (-50 to 50°C)	5.0E-5	cm/cm/°C	ASTM E831
Injection instructions			
Back Pressure: minimum			
NOTE			
1.	Tensile test speed = 2 in/min (50 mm/min)		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

