

# HiFill® PP GB10

Polypropylene  
Techmer Engineered Solutions

Message:  
HiFill® PP GB10 is a Polypropylene product filled with 10% glass bead. It can be processed by injection molding and is available in North America.

General Information			
Filler / Reinforcement	Glass Bead,10% Filler by Weight		
Appearance	Colors Available		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.968	g/cm <sup>3</sup>	ASTM D792
Molding Shrinkage - Flow (3.18 mm)	1.8	%	ASTM D955
Water Absorption (24 hr)	0.010	%	ASTM D570
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	92		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Break)	27.6	MPa	ASTM D638
Tensile Elongation (Break)	10	%	ASTM D638
Flexural Modulus	1380	MPa	ASTM D790
Flexural Strength	34.5	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, 3.18 mm)	27	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed	110	°C	
1.8 MPa, Unannealed	57.2	°C	
Melting Temperature	170	°C	
CLTE - Flow	6.8E-5	cm/cm/°C	ASTM D696
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	1.0E+16	ohms · cm	ASTM D257
Dielectric Strength <sup>1</sup>	20	kV/mm	ASTM D149
NOTE			
1.	Method A (Short-Time)		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

# Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

