

TAISOX 7130F

Ethylene Vinyl Acetate Copolymer

Formosa Plastics Corporation

Message:

TAISOX 7130F is an ethylene vinyl acetate copolymer (EVA) material. This product is available in North America, Europe or Asia Pacific.

The main features of TAISOX 7130F are:

Copolymer

Good processability

Good toughness

The typical application fields of TAISOX 7130F are: movies

General Information			
Features	Copolymer		
	Workability, good		
	Good toughness		
	General		
Uses	Films		
	General		
Forms	Particle		
Physical	Nominal Value	Unit	Test Method
Density	0.930	g/cm ³	ASTM D1505
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	0.90	g/10 min	ASTM D1238
Vinyl Acetate Content	9.0	wt%	
Hardness	Nominal Value	Unit	Test Method
	45		
Durometer Hardness (Shore A)	95		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength			ASTM D638
Yield	5.88	MPa	ASTM D638
Fracture	17.7	MPa	ASTM D638
Tensile Elongation (Break)	650	%	ASTM D638
Flexural Modulus	24.5	MPa	ASTM D790
Coefficient of Friction (Blown Film)	0.50		ASTM D1894
Films	Nominal Value	Unit	Test Method
Film Thickness - Tested	50	µm	
Film Thickness - Recommended / Available	1.2-5.9 mil (30-150 µ)		
secant modulus			ASTM D882

1% secant, MD: 50 µm, blown film	34.3	MPa	ASTM D882
1% secant, TD: 50 µm, blown film	39.2	MPa	ASTM D882
Tensile Strength			ASTM D882
MD: Yield, 50 µm, blown film	4.90	MPa	ASTM D882
TD: Yield, 50 µm, blown film	3.92	MPa	ASTM D882
MD: Broken, 50 µm, blown film	29.4	MPa	ASTM D882
TD: Broken, 50 µm, blown film	27.5	MPa	ASTM D882
Tensile Elongation			ASTM D882
MD: Broken, 50 µm, blown film	400	%	ASTM D882
TD: Broken, 50 µm, blown film	550	%	ASTM D882
Dart Drop Impact (50 µm, Blown Film)	550	g	ASTM D1709
Elmendorf Tear Strength			ASTM D1922
MD: 50 µm, blown film	20	g	ASTM D1922
TD: 50 µm, blown film	48	g	ASTM D1922
Thermal	Nominal Value	Unit	Test Method
Brittleness Temperature	-70.0	°C	ASTM D746
Vicat Softening Temperature	80.0	°C	ASTM D1525
Melting Temperature	93.0	°C	
Optical	Nominal Value	Unit	Test Method
Gloss (45°, 50.0 µm, Blown Film)	80		ASTM D2457
Haze (50.0 µm, Blown Film)	5.0	%	ASTM D1003
Additional Information			

Film extrusion preparation parameters:

Screw: 60 mm

L/D: 30

Blow up ratio: 2.5

Temperature 160 to 200°C

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

