

TAROLOX 2050 W G3

Polybutylene Terephthalate + PET

Taro Plast S.p.A.

Message:

PBT/PET alloy 15% glass fibres reinforced, very good surface appearance, high temperature and chemical resistance. High dimensional stability with low moisture absorption.

General Information			
Filler / Reinforcement	Glass fiber reinforced material, 15% filler by weight		
Features	Good dimensional stability		
	Low hygroscopicity		
	Good chemical resistance		
	Heat resistance, high		
	Good appearance		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Density	1.44	g/cm ³	ISO 1183
Molding Shrinkage			Internal method
Vertical flow direction	0.60 - 1.0	%	Internal method
Flow direction	0.50 - 0.80	%	Internal method
Water Absorption (23°C, 24 hr)	0.050	%	ISO 62
Granule Humidity ¹		%	
Reinforcement Content ² (750°C)	15	%	ISO 3451
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Break)	85.0	MPa	ISO 527-2/50
Tensile Strain (Break)	3.0	%	ISO 527-2/50
Flexural Modulus ³	5400	MPa	ISO 178
Flexural Stress ⁴	115	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	5.0	kJ/m ²	ISO 179/1eA
Notched Izod Impact (23°C)	50	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature ⁵			
0.45 MPa, not annealed	210	°C	ISO 75-2/B
1.8 MPa, not annealed	190	°C	ISO 75-2/A
Continuous Use Temperature ⁶	130	°C	IEC 60216
Vicat Softening Temperature	200	°C	ISO 306/B50
Ball Pressure Test (215°C)	Pass		IEC 60695-10-2
Electrical	Nominal Value	Unit	Test Method

Dielectric Strength (3.20 mm)	24	kV/mm	IEC 60243-1
Comparative Tracking Index (Solution A)	250	V	IEC 60112
Flammability	Nominal Value	Unit	Test Method
Flame Rating (1.60 mm)	HB		UL 94
Glow Wire Flammability Index (2.00 mm)	650	°C	IEC 60695-2-12
Oxygen Index	20	%	ASTM D2863
Injection	Nominal Value	Unit	
Drying Temperature	110 - 130	°C	
Drying Time	2.0	hr	
Processing (Melt) Temp	250 - 280	°C	
Mold Temperature	90.0 - 130	°C	
Injection Rate	Moderate-Fast		
Injection instructions			
Pre-heat Temperature: 130 to 150°CPre-heat Time: 2 to 3 hr			
NOTE			
1.	TARO 002		
2.	1 hr		
3.	1.0 mm/min		
4.	1.0 mm/min		
5.	120°C/hr		
6.	20,000 hr		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT