

elitel UE3500

Thermoplastic Copolyester Elastomer

UNITIKA Plastics Division

Message:

UNITIKA elitel resins are thermoplastic saturated copolymeric polyester resins. With the various excellent properties, elitel resins are expanding their applications from products such as adhesives, paints, ink binders, and modifying agents to the products in new-generation high-tech fields.

Characteristics

elitel products have superior adhesiveness and coatability compared to various materials. They exhibit excellent adhesiveness and coatability to a variety of materials: films and molded products of plastic materials such as polyester, polyvinylchloride, polycarbonate, and cellulose acetate; steel materials such as steel plates; metal materials such as copper, and aluminum; woven or nonwoven fabrics from polyester and other fibers; papers, woods, and others. elitel products may be hardened by combined use of a hardening agent. In this manner, the excellent hardness, film properties, and heat-resisting properties may be further improved.

Blending of an elitel resin with another elitel resin or a different resin provides alloys with more diversified resin properties. Additionally, elitel products are effective as a modifying resin for providing other resins with flexibility, coatability, toughness, and others.

elitel resins form films excellent in flexibility, electrical properties, weather resistance, as well in appearance and transparency.

elitel resins retain consistent quality with smaller change in quality over time.

They are also excellent hygienically

General Information			
Features	Pure/High Purity		
	High molecular weight		
	High strength		
	Copolymer		
	Good electrical performance		
	Good flexibility		
	Good adhesion		
	Good weather resistance		
	Heat resistance, medium		
	Good toughness		
	Soft		
	Extended tensile rate		
	Excellent appearance		
	Medium transparency		
Uses	Films		
	Mixing		
	Coating application		
	Adhesive		
Appearance	Beige		
Forms	flake		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.23	g/cm ³	ASTM D792

Water Absorption (equilibrium, 25°C, 60% RH)	0.50	%	ASTM D570
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore D)	60		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Break)	31.4	MPa	ASTM D638
Tensile Elongation (Break)	1500	%	ASTM D638
Thermal	Nominal Value	Unit	Test Method
Glass Transition Temperature	35.0	°C	DSC
Vicat Softening Temperature	145	°C	ASTM D1525
Electrical	Nominal Value		Test Method
Dielectric Constant	4.50		IEC 60250
Dissipation Factor	0.020		IEC 60250
Fill Analysis	Nominal Value	Unit	Test Method
Melt Viscosity (200°C)	700	Pa·s	ASTM D3835
Additional Information			

Molecular Weight, VPO Method: 30000Limiting Viscosity, Phenol/tetrachloroethane: 0.95Hydroxyl Value:4 mgKOH/gAcid Value: 1 mgKOH/gSolubility parameter: 10.0

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

