

Rilsan® CLEAR G 830 Rnew MED

Polyamide 11

Arkema

Message:

Rilsan ® Clear G830 Rnew MED is a high performance transparent polyamide having outstanding purity level and partially based on renewable resources. This grade offers the highest quality and is specifically designed to meet the stringent requirements of the medical applications. Upon request letters regarding USP Class VI compliance can be provided.

MAIN APPLICATIONS

Dental accessories.

Breathing mask.

Medical perfusion tube accessories.

General Information			
Features	Renewable Resource Content		
Uses	Medical/Healthcare Applications Tubing		
Appearance	Clear/Transparent		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	1.01	g/cm ³	ISO 1183
Molding Shrinkage			Internal Method
Across Flow : 40°C, 24 hr, 4.00 mm	0.51	%	
Flow : 40°C, 24 hr, 4.00 mm	0.46	%	
Water Absorption			ISO 62
23°C, 24 hr	3.3	%	
Equilibrium, 23°C, 50% RH	1.3	%	
Hardness	Nominal Value	Unit	Test Method
Shore Hardness			ISO 868
Shore D	83		
Shore D, 15 sec	81		
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	1690	MPa	ISO 527-2
Tensile Stress			ISO 527-2
Yield	55.0	MPa	
Break	60.0	MPa	
Tensile Strain			ISO 527-2
Yield	7.0	%	
Break	> 150	%	
Flexural Modulus	1530	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179

-30°C	10	kJ/m ²	
23°C	11	kJ/m ²	
Charpy Unnotched Impact Strength			ISO 179
-30°C	No Break		
23°C	No Break		
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, Unannealed	110	°C	ISO 75-2/B
1.8 MPa, Unannealed	95.0	°C	ISO 75-2/A
Glass Transition Temperature	135	°C	ISO 11357-2
Flammability	Nominal Value	Test Method	
Flame Rating (1.50 to 1.65 mm)	HB	UL 94	
Optical	Nominal Value	Unit	Test Method
Transmittance (2000 μm, 560 nm)	91.5	%	ASTM D1003
Additional Information	Nominal Value	Unit	Test Method
Renewable Carbon Content	53 to 55	%	ASTM D6866
Injection	Nominal Value	Unit	
Drying Temperature	90.0	°C	
Drying Time	4.0 to 6.0	hr	
Processing (Melt) Temp	250 to 300	°C	
Mold Temperature	20.0 to 80.0	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT