

SABIC® SUPEER™ 8118L

Metallocene Linear Low Density Polyethylene

Saudi Basic Industries Corporation (SABIC)

Message:

SABIC® SUPEER™ 8118L is an ethylene-octene copolymer produced via Nexlene™ Technology. It performs well in a wide range of general purpose and high performance LLDPE blown film applications and has good processability.

Application

Typical applications for SABIC® SUPEER™ 8118L are lamination film, frozen bags, liquid pouches, heavy duty bags, industrial liner, agriculture film, stretch hood, surface protective film.

This product is not intended for and must not be used in any pharmaceutical/medical applications.

General Information			
Additive	Anti-caking agent slip agent		
Features	Low density Copolymer smoothness Anti-caking property Workability, good Octene comonomer		
Uses	Blown Film Laminate Lining Bags Industrial application Stretch winding Agricultural application General Heavy packing bag		
Processing Method	Blow film		
Physical	Nominal Value	Unit	Test Method
Density	0.918	g/cm ³	ASTM D1505
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	1.1	g/10 min	ASTM D1238
Films	Nominal Value	Unit	Test Method
Film Thickness - Tested	50	µm	ASTM D882
secant modulus			
1% secant, MD: 50 µm, blown film	140	MPa	
1% secant, TD: 50 µm, blown film	156	MPa	ASTM D882

Tensile Strength			ASTM D882
MD: Yield, 50 µm, blown film	12.0	MPa	ASTM D882
TD: Yield, 50 µm, blown film	11.0	MPa	ASTM D882
MD: Broken, 50 µm, blown film	54.0	MPa	ASTM D882
TD: Broken, 50 µm, blown film	54.0	MPa	ASTM D882
Tensile Elongation			ASTM D882
MD: Broken, 50 µm, blown film	630	%	ASTM D882
TD: Broken, 50 µm, blown film	730	%	ASTM D882
Dart Drop Impact ¹ (50 µm, Blown Film)	1000	g	ASTM D1709
Elmendorf Tear Strength			ASTM D1922
MD: 50 µm, blown film	14	g	ASTM D1922
TD: 50 µm, blown film	22	g	ASTM D1922
Thermal	Nominal Value	Unit	Test Method
Melting Temperature	115	°C	Internal method
Optical	Nominal Value	Unit	Test Method
Haze (50.0 µm, Blown Film)	10	%	ASTM D1003
Additional Information	Nominal Value	Unit	
Blown Film Melt Temperature	180 - 200	°C	
Blow-up Ratio	2.00 - 3.00		
Properties have been measured on blown film of 50 µm and BUR = 2.5			
NOTE			
1.	F50		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

