

POLYPRO® SB9302

Polypropylene Copolymer

YUHWAKorea Petrochemical Ind. Co., Ltd.

Message:

POLYPRO® SB9302 is a Polypropylene Copolymer (PP Copolymer) material. It is available in Asia Pacific for injection molding.

Important attributes of POLYPRO® SB9302 are:

RoHS Compliant

Copolymer

Impact Resistant

Typical applications include:

Business/Office Goods

Food Contact Applications

Household Applications

Housings

General Information			
Features	Block Copolymer		
	Good Impact Resistance		
Uses	Battery Cases		
	Household Goods		
	Stationary Supplies		
Agency Ratings	FDA Food Contact, Unspecified Rating		
RoHS Compliance	RoHS Compliant		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	0.910	g/cm ³	ASTM D1505
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	2.0	g/10 min	ASTM D1238
Molding Shrinkage - Flow	1.4 to 1.8	%	Internal Method
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	83		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	25.5	MPa	ASTM D638
Tensile Elongation (Break)	> 500	%	ASTM D638
Flexural Modulus	1180	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			ASTM D256
-20°C	59	J/m	
25°C	590	J/m	
Thermal	Nominal Value	Unit	Test Method

Deflection Temperature Under Load (1.8 MPa, Unannealed)	100	°C	ASTM D648
Vicat Softening Temperature	152	°C	ASTM D1525
Peak Melting Temperature	165	°C	ASTM D3418

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

