

Axiall PVC 8752

Flexible Polyvinyl Chloride

Axiall Corporation

Message:

Low gravity, flame retardant extrusion compound.

General Information			
Additive	Flame Retardant		
Features	Flame Retardant		
	Low Density		
Forms	Pellets		
Processing Method	Extrusion		
Hardness	Nominal Value	Test Method	
Durometer Hardness ¹ (Shore A)	71 to 77	ASTM D2240	
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength			ASTM D638
--	17.6	MPa	
100% Strain	6.89	MPa	
Tensile Elongation (Break)	400	%	ASTM D638
Thermal	Nominal Value	Unit	Test Method
Brittleness Temperature	-40.0	°C	ASTM D746
Flammability	Nominal Value	Unit	Test Method
Oxygen Index	25	%	ASTM D2863
NOTE			
1.	Delayed		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT