

LG EVA ES28005

Ethylene Vinyl Acetate Copolymer

LG Chem Ltd.

Message:

- Applications
- Foam Compound
- Performance
- Uniform VA Contents and MI
- strict contaminant control
- Excellent mechanical properties

General Information			
Uses	Foam		
Physical	Nominal Value	Unit	Test Method
Density	0.951	g/cm ³	ASTM D1505
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	5.0	g/10 min	ASTM D1238
Vinyl Acetate Content	28.0	wt%	
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A)	79		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength ¹ (Break)	13.5	MPa	ASTM D638
Tensile Elongation ² (Break)	800	%	ASTM D638
Thermal	Nominal Value	Unit	Test Method
Vicat Softening Temperature	46.0	°C	Internal method
Melting Temperature	72.0	°C	Internal method
NOTE			
1.	500 mm/min		
2.	500 mm/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT