

Gebablend 65

Polycarbonate + ABS

geba Kunststoffcompounds GmbH

Message:

PC/ABS type with high impact unnotched and notched impact strength

Applications:

technical injection molded parts for various sectors (Automotive, Electrical, Electronic, Mechanical)

General Information			
Features	High Impact Resistance		
Uses	Automotive Applications		
	Electrical/Electronic Applications		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	1.14	g/cm ³	ISO 1183
Melt Volume-Flow Rate (MVR) (260°C/5.0 kg)	23.0	cm ³ /10min	ISO 1133
Molding Shrinkage	0.45 to 0.80	%	
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	2300	MPa	ISO 527-2/1/1
Tensile Stress (Yield)	50.0	MPa	ISO 527-2/50
Tensile Strain (Yield)	5.5	%	ISO 527-2/50
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179/1eA
-30°C	28	kJ/m ²	
23°C	38	kJ/m ²	
Charpy Unnotched Impact Strength			ISO 179/1eU
-30°C	No Break		
23°C	No Break		
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, Unannealed	122	°C	ISO 75-2/B
1.8 MPa, Unannealed	102	°C	ISO 75-2/A
Vicat Softening Temperature	120	°C	ISO 306/B50
Injection	Nominal Value	Unit	
Drying Temperature - Dry Air Dryer	80.0 to 100	°C	
Drying Time - Dry Air Dryer	2.0 to 4.0	hr	
Suggested Max Moisture	0.050	%	
Rear Temperature	240 to 260	°C	
Middle Temperature	250 to 270	°C	

Front Temperature	250 to 280	°C
Nozzle Temperature	250 to 280	°C
Processing (Melt) Temp	250 to 280	°C
Mold Temperature	70.0 to 100	°C

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

