

KRATON® G2832 GS-N

Styrene Ethylene Butylene Styrene Block Copolymer

Kraton Polymers LLC

Message:

Kraton G2832 GS-N is an easy processing, 49 Shore A hardness material designed for film applications. It is supplied from North America in the physical form identified below.

Kraton G2832 GS-N - supplied as a dusted, dense pellet

General Information			
Features	Block Copolymer		
	Good Processability		
Uses	Film		
Forms	Pellets		
Processing Method	Film Extrusion		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.910	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (200°C/5.0 kg)	13 to 21	g/10 min	ASTM D1238
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A)	44 to 54		Internal Method
Films	Nominal Value	Unit	Test Method
Tear Propagation Resistance	17	kN/m	ASTM D1922
Elastomers	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	10.4	MPa	ASTM D412
Tensile Elongation (Break)	610	%	ASTM D412

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT