

Sumiliteresin® PR-50869B

Phenolic

SBHPP

Message:

Straight (unmodified) phenolic resin

Two-step type powder resin

Application

PR-50869B is suitable for the binder of grinding wheels, friction, refractory, carbon material, and suchlike.

PR-50869B is medium flow, high hexa powder phenolic resin. It is designed for the universal use with excellent properties.

General Information		
Features	Medium liquidity	
Uses	Adhesive	
Forms	Powder	
Physical	Nominal Value	Unit
Flow Length (125°C)	3.60	cm
Hexa	13	%
Screen Mesh - 106µm	0.50	%
Thermal	Nominal Value	Unit
Melting Temperature	91.0	°C
Uncured Properties	Nominal Value	Unit
Gel Time (150°C)	1.8	min

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material


Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China


WECHAT