

ALFATER XL® D50E 1SK0011

Thermoplastic Vulcanizate

ALBIS PLASTIC GmbH

Message:

ALFATER XL® D50E 1SK0011 is a Thermoplastic Vulcanizate (TPV) product. It can be processed by blow molding or extrusion and is available in Asia Pacific, Europe, or North America. Applications of ALFATER XL® D50E 1SK0011 include automotive, construction applications, electrical/electronic applications, sealing applications and wire & cable.

Characteristics include:

REACH Compliant

RoHS Compliant

Good Weather Resistance

General Information	
Features	Alkali Resistant
	Good Weather Resistance
	Ozone Resistant
Uses	Automotive Applications
	Blow Molding Applications
	Cable Jacketing
	Construction Applications
	Electrical/Electronic Applications
	Profiles
	Seals
Agency Ratings	EC 1907/2006 (REACH)
RoHS Compliance	RoHS Compliant
Processing Method	Blow Molding
	Extrusion

Physical	Nominal Value	Unit	Test Method
Density	0.940	g/cm ³	ISO 1183
Hardness	Nominal Value	Unit	Test Method
Shore Hardness (Shore D)	50		ISO 868
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (100% Strain)	14.0	MPa	ISO 527-2
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress (Yield)	28.0	MPa	ISO 37
Tensile Elongation (Break)	750	%	ISO 37
Tear Strength	100	kN/m	ISO 34-1
Compression Set ¹ (100°C, 22 hr)	80	%	ISO 815
Thermal	Nominal Value	Unit	

Service Temperature	-40 to 125	°C
Injection	Nominal Value	Unit
Drying Temperature	70.0 to 80.0	°C
Drying Time	2.0 to 4.0	hr
Extrusion	Nominal Value	Unit
Melt Temperature	195 to 215	°C
NOTE		
1.	25%	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

