

VICTREX® PEEK 450CA40

Polyetheretherketone

Victrex plc

Message:

High performance thermoplastic material, 40% carbon fibre reinforced PolyEtherEtherKetone (PEEK), semi crystalline, granules for injection moulding and extrusion, low flow, FDA food contact compliant, colour black.

Applications for higher strength and stiffness in a static or dynamic system. Excellent wear resistance, low coefficient of friction, low coefficient of thermal expansion. Chemically resistant to aggressive environments.

General Information			
UL YellowCard	E161131-531783		
Filler / Reinforcement	Carbon fiber reinforced material, 40% filler by weight		
Features	Semicrystallization		
	Low friction coefficient		
	Rigidity, high		
	High strength		
	Low liquidity		
	Good chemical resistance		
	Good wear resistance		
	Compliance of Food Exposure		
Agency Ratings	FDA Food Exposure, Not Rated		
Appearance	Black		
Forms	Particles		
Processing Method	Extrusion		
	Injection molding		
Physical	Nominal Value	Unit	Test Method
Density ¹	1.44	g/cm³	ISO 1183
Spiral Flow	6.50	cm	Internal method
Molding Shrinkage ²			ISO 294-4
Vertical flow direction	0.50	%	ISO 294-4
Flow direction: 200°C	0.10	%	ISO 294-4
Water Absorption			ISO 62
23°C, 24 hr, 3.20 mm	0.030	%	ISO 62
Balance, 23°C, 3.20mm, 50% RH	0.30	%	ISO 62
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore D, 23°C)	88		ISO 868
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus (23°C)	35000	MPa	ISO 527-2
Tensile Stress (Break, 23°C)	270	MPa	ISO 527-2

Tensile Strain (Break, 23°C)	1.4	%	ISO 527-2
Flexural Modulus (23°C)	30000	MPa	ISO 178
Flexural Stress (23°C)	400	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	10	kJ/m ²	ISO 180/A
Unnotched Izod Impact Strength (23°C)	45	kJ/m ²	ISO 180
Thermal	Nominal Value	Unit	Test Method
Glass Transition Temperature	143	°C	ISO 3146
Melting Temperature	343	°C	ISO 11357-3
Linear thermal expansion coefficient			ISO 11359-2
Flow: < 143°C	5.0E-6	cm/cm/°C	ISO 11359-2
Flow: > 143°C	8.0E-6	cm/cm/°C	ISO 11359-2
Lateral: < 143°C	3.5E-5	cm/cm/°C	ISO 11359-2
Lateral: > 143°C	9.0E-5	cm/cm/°C	ISO 11359-2
Specific Heat Capacity	1800	J/kg/°C	DSC
Toxicity			NES 713
CO Content	0.0500		NES 713
CO2 Content	0.120		NES 713
Total Gases	0.170		NES 713
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity ³ (23°C)	1.0E+5	ohms·cm	ASTM D4496
Flammability	Nominal Value	Unit	Test Method
Glow Wire Flammability Index (2.00 mm)	960	°C	IEC 60695-2-12
Fill Analysis	Nominal Value	Unit	Test Method
Melt Viscosity (400°C)	850	Pa·s	ISO 11443
Injection	Nominal Value	Unit	
Drying Temperature	120 - 150	°C	
Drying Time	3.0 - 5.0	hr	
Hopper Temperature	< 100	°C	
Rear Temperature	380	°C	
Middle Temperature	390 - 395	°C	
Front Temperature	400	°C	
Nozzle Temperature	405	°C	
Mold Temperature	190 - 210	°C	
Injection instructions			
Runner: Die / nozzle >3mm, manifold >3.5mmGate: >2mm or 0.5 x part thickness			
NOTE			
1.	Crystalline		
2.	405°C nozzle		
3.	1V		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any

infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

