

SIBUR Synthetic Rubber SBR-1723 Grade A

Emulsion Styrene Butadiene Rubber

SIBUR

Message:

Oil-extended styrene butadiene synthetic rubber SBR-1723 TDAE is essentially a styrene (23.5%) and butadiene (76.5%) copolymer obtained by emulsification method with the use of resin/fatty soaps. The copolymer is filled with oil TDAE. The polymer contains no nitrosamines and substances that may become a source of nitrosamines.

Appearance - bale of dark-brown color; weight of a bale - (30 ± 1) kg; packing - a corrugated board container, a plastic container; shelf life - one (1) year since the date of manufacture

General Information			
Additive	Oxidation resistance (3000 to 7000 ppm)		
Features	Copolymer		
	Antioxidation		
Appearance	Brown		
Forms	bag		
Physical	Nominal Value	Unit	Test Method
Mooney Viscosity (ML 1+4, 100°C)	46 - 52	MU	ASTM D1646
Bound Styrene	22.5 - 24.5	%	Internal method
Oil Content - TDAE	26 - 29	%	ASTM D5774
Organic Acid	4.2 - 5.8	%	ASTM D5774
Soap - Organic Acid		%	ASTM D5774
Solvent Extract Content	29 - 35	%	Internal method
Ash Content		%	ASTM D5667
Volatile Matter		%	ASTM D5668
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress (300% Strain)	> 9.80	MPa	ASTM D3185
Tensile Strength (Yield)	> 18.0	MPa	ASTM D3185
Tensile Elongation (Break)	> 380	%	ASTM D3185

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT