

Niuk 60GP30

Polybutylene Terephthalate

Shanghai Niuk New Plastic Technology Co., Ltd.

Message:

Niuk 60GP30 is a Polybutylene Terephthalate (PBT) material filled with 30% glass fiber. It is available in Asia Pacific.

Important attributes of Niuk 60GP30 are:

- Flame Rated
- Corrosion Resistant
- Heat Resistant
- Low Moisture Absorption
- Rigid

Typical applications include:
Electrical/Electronic Applications
Engineering/Industrial Parts

General Information	
Filler / Reinforcement	Glass Fiber,30% Filler by Weight
Features	Good Corrosion Resistance
	Good Electrical Properties
	High Heat Resistance
	High Rigidity
	Low Moisture Absorption
Uses	Connectors
	Electrical/Electronic Applications
	Gears
	Pump Parts
	Switches
	Valves/Valve Parts

Physical	Nominal Value	Unit	Test Method
Density	1.54	g/cm ³	ISO 1183
Molding Shrinkage ¹			ISO 2577
Across Flow : 3.20 mm	0.40 to 0.60	%	
Flow : 3.20 mm	1.0 to 1.1	%	
Ash Content	30	%	ISO 3451
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress	120	MPa	ISO 527-2/50
Tensile Strain (Break)	3.0	%	ISO 527-2/50
Flexural Modulus ²	7200	MPa	ISO 178
Flexural Stress ³	185	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	10	kJ/m ²	ISO 179

Charpy Unnotched Impact Strength (23°C)	50	kJ/m ²	ISO 179
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, Unannealed	215	°C	ISO 75-2/B
1.8 MPa, Unannealed	205	°C	ISO 75-2/A
Vicat Softening Temperature	215	°C	ISO 306/B120
Flammability	Nominal Value		Test Method
Flame Rating (1.60 mm)	HB		UL 94
NOTE			
1.	150x100x3.2 mm		
2.	2.0 mm/min		
3.	2.0 mm/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

