

HIDEN® P601 KUBLR

High Density Polyethylene

YUHW A Korea Petrochemical Ind. Co., Ltd.

Message:

HIDEN® P601 KUBLR is a High Density Polyethylene material. It is available in Asia Pacific.

Important attributes of HIDEN® P601 KUBLR are:

Carbon Black

Good UV Resistance

Good Weather Resistance

Wear Resistant

Typical applications include:

Coating Applications

Plumbing/Piping/Potable Water

General Information			
Additive	Carbon Black (2%)		
Features	Good Abrasion Resistance		
	Good UV Resistance		
	Good Weather Resistance		
Uses	Pipe Coatings		
	Piping		
Appearance	Black		
Physical	Nominal Value	Unit	Test Method
Density	0.949	g/cm ³	ASTM D1505
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	0.43	g/10 min	ASTM D1238
Environmental Stress-Cracking Resistance ¹	> 5000	hr	ASTM D1693B
Carbon Black Content	2.3	%	ISO 6964
Carbon Black Dispersion	< 3		ISO 18553
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore D)	60		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	19.6	MPa	ASTM D638
Tensile Elongation (Break)	> 600	%	ASTM D638
Flexural Modulus	735	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	> 490	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	58.0	°C	ASTM D648
Brittleness Temperature	< -70.0	°C	ASTM D746

Vicat Softening Temperature	121	°C	ASTM D1525
Peak Melting Temperature	131	°C	ASTM D3418
NOTE			
1.	100%		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

