

OXNILON 66 15-IMP

Polyamide 66
Oxford Polymers

Message:

OXNILON 66 15-IMP is a Polyamide 66 (Nylon 66) material. It is available in North America for injection molding. Primary attribute of OXNILON 66 15-IMP: Impact Modified.

General Information			
Additive	Impact Modifier		
Features	Impact Modified		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.08	g/cm ³	ASTM D792
Molding Shrinkage - Flow	2.0	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Break)	51.7	MPa	ASTM D638
Tensile Elongation (Break)	210	%	ASTM D638
Flexural Modulus	1690	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	800	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	71.1	°C	ASTM D648
Melting Temperature	255	°C	
Injection	Nominal Value	Unit	
Drying Temperature	79.4	°C	
Drying Time	4.0	hr	
Rear Temperature	274 to 282	°C	
Middle Temperature	277 to 288	°C	
Front Temperature	282 to 293	°C	
Nozzle Temperature	282 to 293	°C	
Processing (Melt) Temp	282 to 293	°C	
Mold Temperature	65.6 to 107	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

