

Matrixx 30M5401

Polybutylene Terephthalate

The Matrixx Group, Inc.

Message:

Matrixx 30M5401 is a Polybutylene Terephthalate (PBT) material filled with 40% glass\mineral. It is available in North America. Primary attribute of Matrixx 30M5401: Flame Rated.

General Information			
Filler / Reinforcement	Glass\Mineral,40% Filler by Weight		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.62	g/cm ³	ASTM D792
Mechanical	Nominal Value	Unit	Test Method
Flexural Modulus - Tangent (23°C, 3.18 mm)	8270	MPa	ASTM D790
Flexural Strength (Yield, 23°C, 3.18 mm)	103	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, 3.18 mm)	69	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed, 3.18 mm	216	°C	
1.8 MPa, Unannealed, 3.18 mm	199	°C	
RTI Elec	75.0	°C	UL 746
RTI Imp	75.0	°C	UL 746
RTI Str	75.0	°C	UL 746
Flammability	Nominal Value		Test Method
Flame Rating (1.50 mm)	HB		UL 94
Additional Information	Nominal Value	Unit	Test Method
Reinforcement Content	40	%	ASTM D5630

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT